



# TerraPrime RedLine

## Technical Data Sheet

### Product Description

**TerraPrime RedLine** is designed to be used as a quick cure concrete sealer or as a primer for systems such as **TerraChip®**, **TerraQuartz®** or **TerraTono™**. It has excellent adhesion to concrete and provides a faster curing time than standard **TerraPrime**.

**TerraPrime RedLine** is a two component 100% solids epoxy coating cured with a polyamine. It is generally supplied clear.

### Features and Benefits

**Excellent Adhesion:** Versatile Primer

**Low Temperature Cure:** Can be applied at 45°F

**Quick Curing:** Less downtime before final coating application.

**Nonporous:** Prevents chemical migration to the substrate which can cause disbonding and environmental contamination.

**100% Solids:** Low odor makes it ideal for use in Pharmaceutical and Food & Beverage facilities.

### Applications

Pharmaceutical Plants  
Food and Beverage Plants  
Commercial Kitchens  
Dairies  
Wastewater Treatment  
Loading Docks  
Warehouses  
Production Lines

### Application Overview

#### Environment

Apply when air, surface, and material temperatures are between 45°F and 90°F. The surface temperature must be at least 5° above the dew point to prevent moisture condensation.

#### Substrate

The concrete must be structurally sound and free of oil, grease, and other contaminants. When applying directly to concrete, the concrete must first be prepared by shot blasting, scarifying or acid etching to create a surface profile equivalent to 40-60 grit sandpaper.

#### Mixing

Part “A” should be mechanically pre-mixed for 60 seconds before adding Part “B”. After adding Parts “A” and “B” together, mix for 90 seconds. Do not hand mix.

#### Application

Immediately pour activated product on the substrate and, using a squeegee, pull out the material at the desired coverage rate.

#### Rolling

Using a 3/8” nap, non-shedding roller, roll the product in both directions to ensure even coverage.

#### Recoating

If additional coats are desired, they must be applied within 10 hours, or the cured material must be sanded before application.

### Recommended Uses

- Concrete Sealer
- Build Coat for anti-skid systems
- Primer for thin film and decorative systems.

The technical data and suggestions presented here are believed to be reliable and accurate at the time of publication. American Industrial makes no warranty, expressed or implied, based on this literature. Published technical data and recommendations are subject to change without notice.

## Product Limitations

### Rising Temperatures

Concrete will outgas during periods of rising temperatures. To prevent bubbling, always apply when the application and cure temperatures will be constant or decreasing.

### Cracks

Moving cracks in the substrate are likely to transfer to the coating unless treated properly.

### Moisture

All concrete surfaces should be tested for moisture before applying a seamless coating. Water vapor transmission upwards through on-grade (or below grade) concrete slabs may result in system failure. If moisture emissions exceed 3 lbs./1000 sq. ft./24 hours, use of TerraPrime MM may be required prior to application of the coating system. Contact the manufacturer before application.

## Safety

This product is intended to be installed by experienced professionals. Read the MSDS and product label for complete safety information before using. Avoid contact with all materials to prevent irritation. Use only with adequate ventilation.

Safety glasses, gloves, and protective clothing should be worn at all times while handling this product. Avoid exposure to eyes and skin as isocyanate resins and amine hardeners can cause mild to severe skin irritation.

## Maintenance

Do not wash the floor within 5 days of installation. Exposure to water before the floor is completely cured may dull the finish. Damp mop as needed with a clean mop head and clean, warm water with a mild detergent or degreaser. Rinse thoroughly to avoid leaving residue. When using a new cleaner for the first time, test clean an inconspicuous area to ensure compatibility with the floor.

## Storage

Store material in a cool, dry location away from flames. When stored properly, the shelf life will be a minimum of 1 year.

## Warranty

American Industrial warrants its products to be free of defects in material and workmanship. This warranty specifically excludes the following: problems due to irregularities in the substrate, failures caused by moisture migration through the substrate, changes in color and gloss. Claims must be made within 12 months of installation of material.

## Physical Properties

<b>Components</b>	2	
<b>Mix Ratio (A:B)</b>	2:1	
<b>Solids</b>	100%	
<b>Packaging</b>	3 gallon kit	2 gal A/1 gal
<b>Coverage</b>	125-200 sqft/gallon	
<b>Application Temperature</b>	45°F-90°F	
<b>Viscosity (mixed)</b>	550 cps	
<b>Pot Life (1 gallon-72°F)</b>	15 minutes	
<b>Working Time (72°F)</b>	15 minutes	
<b>Cure Time (Std.)</b>	4 hours (foot traffic) 4-10 hours (recoat)	
<b>Flash Point</b>	Part A: >200°F Part B: >200°F	
<b>Shelf Life</b>	12 months	
<b>USDA: Food and Beverage</b>	Meets requirements.	

## Performance Properties

<b>Adhesion</b> (ASTM D-4541)	>250 psi (concrete fails)
<b>Hardness</b> (ASTM D-2240)	84 Shore D
<b>Abrasion Resistance</b> (ASTM D-4060) cs-17 wheels, etc	74 mgs.
<b>Maximum Service Temperature</b>	170°F

The technical data and suggestions presented here are believed to be reliable and accurate at the time of publication. American Industrial makes no warranty, expressed or implied, based on this literature. Published technical data and recommendations are subject to change without notice.